

Designation	DIN	EN Nr.	UNS (ASTM)	AISI	WCA
CuZn23Al3Co	-	CW703R	C68800	-	610

Chemical composition

Zn	Cu	Al	Co	Fe	Ni	Pb	Sn	Others
Balance	72.0 - 75.0	3.00 - 3.80	0.25 - 0.55	≤ 0.05	≤ 0.30	≤ 0.05	≤ 0.10	≤ 0.10

Values (Weight %). In order to achieve maximum homogeneity and consistent quality, the actual manufacturing tolerances are tighter and more precisely than the composition indicated.

Main technical properties and features

The CuZn23Al3Co is a special copper-zinc brass containing Al and Co as additional alloying elements. Additions of aluminum and trace of cobalt improve the tensile strength, the corrosion resistance (in sea water for example), fatigue strength and the thermal stress relaxation. The CuZn23Al3Co presents good strength, a non-directional formability and a bendability on the same level as the CuSn6. The alloy has an %IACS 3 to 4 % higher than the CuSn6 alloy, and is specially used for electrical interconnectors.

Typical uses

The CuZn23Al3Co brass is used in many different applications, carries, insulators, transistor, switches, stamped-bent parts, contact springs, electrical connectors, relays and many electronic applications.

Typical manufacturing range

		Thickness (mm)	Width (mm)	Length (mm)
Rolled products	Strip in coils ^[1]	0.10 - 1.50	8.00 - 143	-
	Strip as sheets ^[1]	0.10 - 1.50	8.00 - 110	500 - 3000

^[1] Not all our production possibilities are presented here. Other dimensions or product forms available upon request. Some combinations of thicknesses and widths are not possible.

Mechanical properties of strips

Temper			R _{p0.2} (N/mm ²)	R _m (N/mm ²)	A _{50mm} (%)	Hardness HV
R540	H170	soft	430 max.	540 - 600	30 min.	170 - 220
R630	H195	hard	500 min.	630 - 800	7 min.	195 - 250
R800	H240	extra hard	750 min.	800 min.	-	240 min.

Physical properties

Modulus of elasticity	kN/mm ²	116
Poisson ratio		0.34
Density	g/cm ³	8.20
Melting point	°C	950
Linear dilatation coefficient (0 - 300°C)	10 ⁻⁶ /°C	18.2
Thermal capacity (C _p) at 20°C	kJ/kg K	0.377
Thermal conductivity at 20°C	W/m °K	69
Electrical resistivity (0 - 300°C)	μΩcm	9.6
Electrical conductivity	MS/m	10
Electrical conductivity	% IACS	17
Magnetic properties		Non magnetic

Tolerances (strip and foil)

Thickness	Thickness (mm)		EN Standard		Weber Calibra		
	≥	<	10140 Precision	10258 Precision	WCA Standard	WCA Precision	WCA Extreme
<p>The table shown is an outline of our typical thickness tolerances available. They are tighter than industry standards.</p> <p>Our "WCA Precision" and "WCA Extreme" tolerances are available upon request.</p>	0.100	0.125	± 0.005	± 0.006	± 0.005	± 0.004	± 0.003
	0.125	0.150	± 0.005	± 0.006	± 0.005	± 0.005	± 0.004
	0.150	0.250	± 0.010	± 0.008	± 0.008	± 0.006	± 0.004
	0.250	0.300	± 0.010	± 0.009	± 0.009	± 0.007	± 0.005
	0.300	0.400	± 0.010	± 0.010	± 0.010	± 0.007	± 0.005
	0.400	0.500	± 0.015	± 0.012	± 0.012	± 0.008	± 0.006
	0.500	0.600	± 0.015	± 0.014	± 0.014	± 0.010	± 0.007
	0.600	0.800	± 0.015	± 0.015	± 0.015	± 0.010	± 0.007
	0.800	1.000	± 0.015	± 0.018	± 0.018	± 0.012	± 0.009
	1.000	1.200	± 0.020	± 0.020	± 0.020	± 0.015	± 0.012
Width	Our width tolerances "Standard" is +0.2, -0.0 (or ± 0.1 mm upon request). They are available for slit widths < 125 mm and thicknesses < 1.00 mm. Special tolerances upon request.						
Camber	Width (mm)		Camber max. (mm/m)				
	>	≤	WCA Standard		WCA Extreme		
			≤ 0.5 mm	> 0.5 mm	≤ 0.5 mm	> 0.5 mm	
	3	6	12	-	6	-	
	6	10	8	10	4	5	
10	20	4	6	2	3		
20	143	2	3	1	1.5		
Surface	Special surface qualities upon request						
Flatness	Special requirement on the longitudinal or transversal flatness upon request						

WCA-MK.037 / Edition 2024/02

The provided information in this document is informative without any guarantee. They do not imply any contractual obligation on our behalf.

