

Designation	DIN	EN Nr.	UNS (ASTM)	AISI	WCA
CuZn33	-	CW506L	26800	-	202

Chemical composition

Zn	Cu	Al	Fe	Ni	Pb	Sn	Others
Balance	66 – 68.5	≤ 0.02	≤ 0.05	≤ 0.20	≤ 0.05	≤ 0.05	≤ 0.20

Values (Weight %). In order to achieve maximum homogeneity and consistent quality, the actual manufacturing tolerances are tighter and more precisely than the composition indicated.

Main technical properties and features

The Brass CuZn33 is a lead-free brass alloy containing 67% copper. The microstructure shows an alpha single-phase with a very good behavior for cold formability, polishing, galvanic processes, soft and hard solderability. The brass shows a good resistance to fresh water, neutral or alkaline solutions, organic compounds as well as land, sea and industrial atmosphere. It is not resistant to acids, hydrous sulfur compounds, hydrous ammonia (stress corrosion cracking) in non-stress-relieved condition. The temperature ranges for thermal annealing are about 450-650°C, and 200-300°C for a stress-relieving. The machinability index is estimated around 25% (relative to CuZn39Pb3).

Typical uses

Metal goods, deep drawn parts, stamped and embossed parts, connectors, watch dials.

Typical manufacturing range

	Thickness (mm)	Width (mm)	Length (mm)
Rolled products Strip in coils ^[1]	0.10 - 1.50	3 - 140	-
Strip as sheets ^[1]	0.10 - 1.50	10 - 120	500 - 3000

^[1] Not all our production possibilities are presented here. Other dimensions or product forms available upon request. Some combinations of thicknesses and widths are not possible.

Mechanical properties of strips

Temper			R _{p0.2} (N/mm ²)	R _m (N/mm ²)	A _{50mm} (%)	Hardness HV
R280	H055	soft	170 max.	280 - 380	40 min.	55 - 90
R350	H095	½ hard	170 min.	350 - 430	23 min.	95 - 125
R420	H125	¾ hard	300 min.	420 - 500	6 min.	125 - 155
R500	H155	hard	450 min.	500 min.	-	155 min.

Physical properties

Modulus of elasticity	kN/mm ²	112
Density	g/cm ³	8.50
Melting point	°C	902 - 940
Linear dilatation coefficient	10 ⁻⁶ /°C	19.9
Thermal conductivity at 20°C	W/m °K	121
Thermal capacity at 20°C	J/kg K	377
Electrical resistivity	μΩcm	6.5
Electrical conductivity at 20°C	MS/m	16 ^[1]
Electrical conductivity at 20°C	% IACS	28 ^[1]
Magnetic properties		Diamagnétique

[1] Values for soft temper. The electrical conductivity decrease slightly for higher strain hardening.

Tolerances (strip and foil)

Thickness	Thickness (mm)		EN Standard		WEBER + CALIBRA		
	≥	<	10140 Precision	10258 Precision	WCA Standard	WCA Precision	WCA Extreme
<p>The table shown is an outline of our typical thickness tolerances available. They are tighter than industry standards.</p> <p>Our "WCA Precision" and "WCA Extreme" tolerances are available upon request.</p>	-	0.025	-	-	-	-	± 0.001
	0.025	0.050	-	-	± 0.003	± 0.002	± 0.0015
	0.050	0.065	-	± 0.003	± 0.003	± 0.0025	± 0.002
	0.065	0.100	-	± 0.004	± 0.004	± 0.0035	± 0.003
	0.100	0.125	± 0.005	± 0.006	± 0.005	± 0.004	± 0.003
	0.125	0.150	± 0.005	± 0.006	± 0.005	± 0.005	± 0.004
	0.150	0.250	± 0.010	± 0.008	± 0.008	± 0.006	± 0.004
	0.250	0.300	± 0.010	± 0.009	± 0.009	± 0.007	± 0.005
	0.300	0.400	± 0.010	± 0.010	± 0.010	± 0.007	± 0.005
	0.400	0.500	± 0.015	± 0.012	± 0.012	± 0.008	± 0.006
	0.500	0.600	± 0.015	± 0.014	± 0.014	± 0.010	± 0.007
	0.600	0.800	± 0.015	± 0.015	± 0.015	± 0.010	± 0.007
	0.800	1.000	± 0.015	± 0.018	± 0.018	± 0.012	± 0.009
	1.000	1.200	± 0.020	± 0.020	± 0.020	± 0.015	± 0.012
	1.200	1.250	± 0.020	± 0.020	± 0.020	± 0.015	± 0.012
1.250	1.500	± 0.020	± 0.020	± 0.020	± 0.015	± 0.014	
Width	Our width tolerances "Standard" is +0.2, -0.0 (or ± 0.1 mm upon request). They are available for slit widths < 125 mm and thicknesses < 1.00 mm. Special tolerances upon request.						
Camber	Width (mm)		Camber max. (mm/m)				
<p>Our tolerance "WCA Standard" respects the EN Standard 1654 (Length of measurement 1000 mm). Other tolerances upon request.</p>	>	≤	WCA Standard		WCA Extreme		
			≤ 0.5 mm	> 0.5 mm	≤ 0.5 mm	> 0.5 mm	
	3	6	12	-	6	-	
	6	10	8	10	4	5	
	10	20	4	6	2	3	
20	250	2	3	1	1.5		
Surface	Special surface qualities upon request						
Flatness	Special requirement on the longitudinal or transversal flatness upon request						

WCA-MK.013 / Edition 2024/02

The provided information in this document is informative without any guarantee. They do not imply any contractual obligation on our behalf.

